



钢铁之家

www.steels.org.cn

全球钢号百科!

Global Steel Grade Encyclopedia



涵盖的行业或国家与地区类别



国际材料与试验协会

GJB

国家军用标准



动力机械工程师协会

EU

前欧洲标准化

AISI

美国钢铁学会



德国工业标准

AMS

航空航天材料规范



国际标准

JASO

日本汽车标准组织

EN

欧洲标准

JB

中国机械行业标准

UNS

统一编号系统

UNI

意大利标准



美国机械工程师协会

SS

瑞典标准



国家标准



日本工业标准

Assab Steels ASSAB XW-41 Cold Work Steel

Category : Metal , Ferrous Metal , Carbon Steel , High Carbon Steel , Chrome-moly Steel , Tool Steel , Cold Work Steel

Material Notes:

XW-41 is a high-carbon, high chromium tool steel alloyed with molybdenum and vanadium characterized by:High wear resistanceHigh compressive strength Good through-hardening propertiesHigh stability in hardeningGood resistance to tempering-back.XW-41 is used when cutting thicker, harder materials; when forming with tools subjected to bending stresses and where high impact loads are involved. XW-41 can be supplied in various finishes, including the hot-rolled, pre-machined and fine machined condition. It is also available in the form of hollow bar and rings. AISI D2, W.-Nr. 1.2379

Order this product through the following link:

http://www.lookpolymers.com/polymer_Assab-Steels-ASSAB-XW-41-Cold-Work-Steel.php

Physical Properties	Metric	English	Comments
Density	7.67 g/cc	0.277 lb/in ³	
	7.61 g/cc	0.275 lb/in ³	
	@Temperature 400 °C	@Temperature 752 °F	
	7.64 g/cc	0.276 lb/in ³	
	@Temperature 200 °C	@Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	41	41	1020°C Austenitizing temperature, for tempering at 650°C
	44	44	1050°C Austenitizing temperature, for tempering at 650°C
	55	55	1020°C Austenitizing temperature, for tempering at 550°C
	57	57	1050°C Austenitizing temperature, for tempering at 400°C
	59	59	1020°C Austenitizing temperature, for tempering at 400°C
	60	60	1050°C Austenitizing temperature, for tempering at 200°C
	61	61	At 980°C during hardening, soaking time 30 minutes
	62	62	1050°C Austenitizing temperature, for tempering at 550°C
	62	62	Hardened and tempered.
	62.5	62.5	At 980°C during hardening, soaking time 60 minutes

Mechanical Properties	Metric	English	Comments
	64.25	64.25	At 1060°C during hardening, soaking time 30 minutes
	65	65	At 1020°C during hardening, soaking time 30 minutes
	65.5	65.5	At 1020°C during hardening, soaking time 60 minutes
Modulus of Elasticity	193 GPa	28000 ksi	
	173 GPa	25100 ksi	
	@Temperature 400 °C	@Temperature 752 °F	
Compressive Strength	1900 MPa	276000 psi	HRC 55 R _c 0.2
	2200 MPa	319000 psi	HRC 62 R _c 0.2.

Thermal Properties	Metric	English	Comments
CTE, linear	12.4 µm/m-°C	6.89 µin/in-°F	
	@Temperature 20.0 - 200 °C	@Temperature 68.0 - 392 °F	
	13.4 µm/m-°C	7.44 µin/in-°F	
	@Temperature 20.0 - 400 °C	@Temperature 68.0 - 752 °F	
Specific Heat Capacity	0.460 J/g-°C	0.110 BTU/lb-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	20.0 W/m-K	139 BTU-in/hr-ft ² -°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	21.0 W/m-K	146 BTU-in/hr-ft ² -°F	
	@Temperature 200 °C	@Temperature 392 °F	
	23.0 W/m-K	160 BTU-in/hr-ft ² -°F	
	@Temperature 400 °C	@Temperature 752 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	1.55 %	1.55 %	
Chromium, Cr	11.8 %	11.8 %	
Iron, Fe	84.35 %	84.35 %	
Manganese, Mn	0.40 %	0.40 %	

Component Elements Properties	Metric	English	Comments
Molybdenum, Mo			
Silicon, Si	0.30 %	0.30 %	
Vanadium, V	0.80 %	0.80 %	

